

Optigear BM Range

High Performance Gear Oils

Description

Castrol Optigear™ BM is a range of high-performance extreme pressure gear oils, developed to tackle wear-related problems in heavily loaded industrial gears and bearings.

Optigear BM is formulated with Castrol's Microflux Trans (MFT) Plastic Deformation (PD) additive. MFT PD helps improve performance when operating temperature and loads reach a certain level of activation energy, by enabling the micro-smoothing of surface roughness without increasing wear. The smoothed surface delivers optimum wear protection and an extremely low coefficient of friction, especially in applications which experience extreme pressure, shock loads, vibrations or low speeds. MFT PD helps to protect against scuffing and shock loading, while maintaining a high load carrying capacity, and can help prevent the progression of micro-pitting in pre-damaged gears.

Specific grades within the Optigear BM range meet the requirements of DIN 51517 part 3 CLP and the requirements of a wide range of industrial bodies and equipment manufacturers.

Application

Optigear BM is suitable for gears and bearings operating under normal to extreme conditions. Extreme pressure additives make Optigear BM suitable where there is a need to maintain high load carrying capacity while protecting against scuffing and shock loading.

Advantages

Compared to conventional non-PD oils, Castrol Optigear BM can deliver the following advantages:

- Tests have shown a reduction in the coefficient of friction of up to 60% over conventional oils without PD technology¹ which can deliver energy savings, lower lubricant and component temperatures and improve operational efficiency
- In laboratory tests Castrol PD additives were shown to prevent the progression of micro-pitting in pre-damaged gears. Non-PD oils used in pre-damaged gears showed existing wear levels increased up to three times²
- Smoothing existing gear damage reduces the cost of repairs and replacements and improves operating efficiency by increasing equipment reliability
- Friction, heat and vibration are reduced
- Oil with Castrol PD additives provides superior protection with wear levels of less than half those observed in tests with conventional non-PD oil³ to help extend planned gear and bearing life
- Extended lubricant service life and relubrication intervals can help to reduce costs and waste oil disposal
- Full load operation is achieved in a short time, virtually eliminating the running-in period

¹In-house testing on SRV test rig; steel ball against steel plate.

²In-house modified FZG micro-pitting test.

³Independent MPR testing carried out by Powertrib showed weight loss was less than half that recorded through use of a conventional non-PD oil.

Typical Characteristics

Name	Method	Units	68	100	150	220	320	460	680	1000	1500	3000
Colour	visual	-	Brown									
ISO Viscosity Group	-	-	68	100	150	220	320	460	680	1000	1500	3000
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m ³	890	895	900	905	910	910	920	930	930	930
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	68	100	150	220	320	460	680	1000	1500	3000
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	9.1	11.7	15.0	19.4	24.9	31.8	38.3	47.4	64.2	119.8
Viscosity Index	ISO 2909 / ASTM D2270	-	110	105	100	100	100	100	93	90	95	110
Flash Point - open cup method	ISO 2592 / ASTM D92	°C/°F	220/ 428	220/ 428	225/ 437	230/ 446	235/ 455	240/ 464	245/ 473	250/ 482	235/ 455	220/ 428
Pour Point	ISO 3016 / ASTM D97	°C/°F	-24/-11	-21/-6	-18/0	-15/5	-15/5	-12/-10	-9/16	-9/16	-3/27	0/32
Copper corrosion (3 hrs@100°C/ 212°F)	ISO 2160 / ASTM D130	Rating	1	1	1	1	1	1	1	1	1	1
Rust test - distilled water (24 hrs)	ISO 7120 / ASTM D665A	-	Pass									
Rust test - synthetic seawater (24 hrs)	ISO 7120 / ASTM D665B	-	Pass									
FZG Gear Scuffing test - A/8.3/90	ISO 14635-1	Failure Load Stage			>12	>12*	>12	>12	>12*	>12*	>12*	>12*
FZG Micropitting tests @ 60°C/140°F and 90°C/194°F	FVA 54-7	Failure Load Stage, Micropitting Rating					>10 high					
FE8 Bearing Wear Test (F.562831.01-7.5/80-80)	DIN 51819-3	Roller Wear, mg			<10		<10					

* Data read across from lower viscosity grade Subject to usual manufacturing tolerances.

User Advice

- Miscible and compatible with most mineral oil based gear oils. However, maximum performance is only guaranteed if not mixed with any other product.
- Compatible with non-ferrous metals.
- Compatible with most paints and conventional sealing materials.
- Mechanical cleaning with all known filtering installations and separators possible.

Optigear BM Range
23 Oct 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>